

said resin (C1) is at least one member selected from the group consisting of polyester resins, polyether resins, polycarbonate resins, polyurethane resins, polyolefin resins, acrylic resins, and modifications of these.

8. (amended) The method of forming a coating film according to Claim 1,  
wherein the electrodeposition coating [2] contains a resin (A3) having a sulfonium group,  
an aliphatic hydrocarbon group of 8 to 24 carbon atoms, which optionally contain an unsaturated  
double bond within the chain thereof, and a propargyl group.

10. (amended) The method of forming a coating film according to Claim 8,  
wherein the electrodeposition coating [2] contains a resin (C2) having a number average  
molecular weight of 1,000 to 30,000, and

said resin (C2) is at least one member selected from the group consisting of polyester  
resins, polyether resins, polycarbonate resins, polyurethane resins, polyolefin resins, acrylic  
resins, and modifications of these.

11. (amended) The method of forming a coating film according to Claim 1,  
wherein the electrodeposition coating [1] and the electrodeposition coating [2] each  
contains a metal acetate and/or an acetylacetonate complex as a catalyst, and

said metal is at least one member selected from the group consisting of copper, cerium,  
aluminum, tin, manganese, zinc, cobalt and nickel.

Cont  
A3

12. A coated article having the coating film formed by the method of forming a coating film according to Claim 1.

**Claims 13-20 are added as new claims.**

A4

13. The method of forming a coating film according to Claim 2,  
wherein the resin (A) is at least one resin (A2) selected from the group consisting of polyester resins, polyether resins, polycarbonate resins, polyurethane resins, polyolefin resins, acrylic resins and modifications of these.

099201.12601  
FO921" TFO26660

14. The method of forming a coating film according to Claim 3,  
wherein the electrodeposition coating [1] contains a resin (C1) having a number average molecular weight of 1,000 to 30,000, and  
said resin (C1) is at least one member selected from the group consisting of polyester resins, polyether resins, polycarbonate resins, polyurethane resins, polyolefin resins, acrylic resins, and modifications of these.

15. The method of forming a coating film according to Claim 4,  
wherein the electrodeposition coating [1] contains a resin (C1) having a number average molecular weight of 1,000 to 30,000, and  
said resin (C1) is at least one member selected from the group consisting of polyester resins, polyether resins, polycarbonate resins, polyurethane resins, polyolefin resins, acrylic resins, and modifications of these.

16. The method of forming a coating film according to Claim 9,  
wherein the electrodeposition coating [2] contains a resin (C2) having a number average  
molecular weight of 1,000 to 30,000, and

said resin (C2) is at least one member selected from the group consisting of polyester  
resins, polyether resins, polycarbonate resins, polyurethane resins, polyolefin resins, acrylic  
resins, and modifications of these.

17. The method of forming a coating film according to Claim 2,  
wherein the electrodeposition coating [1] and the electrodeposition coating [2] each  
contains a metal acetate and/or an acetylacetonate complex as a catalyst, and

said metal is at least one member selected from the group consisting of copper, cerium,  
aluminum, tin, manganese, zinc, cobalt and nickel.

18. The method of forming a coating film according to Claim 5,  
wherein the electrodeposition coating [1] and the electrodeposition coating [2] each  
contains a metal acetate and/or an acetylacetonate complex as a catalyst, and

said metal is at least one member selected from the group consisting of copper, cerium,  
aluminum, tin, manganese, zinc, cobalt and nickel.

19. A coated article having the coating film formed by the method of forming a coating  
film according to Claim 2.

PRELIMINARY AMENDMENT  
NEW U.S. APPLICATION

Q67257

Cont  
A4

20. A coated article having the coating film formed by the method of forming a coating  
film according to Claim 5.

0992011-112601  
T09211-T02660